

This Page Is Inserted by IFW Operations  
and is not a part of the Official Record

## **BEST AVAILABLE IMAGES**

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images may include (but are not limited to):

- BLACK BORDERS
- TEXT CUT OFF AT TOP, BOTTOM OR SIDES
- FADED TEXT
- ILLEGIBLE TEXT
- SKEWED/SLANTED IMAGES
- COLORED PHOTOS
- BLACK OR VERY BLACK AND WHITE DARK PHOTOS
- GRAY SCALE DOCUMENTS

**IMAGES ARE BEST AVAILABLE COPY.**

**As rescanning documents *will not* correct images,  
please do not report the images to the  
Image Problem Mailbox.**



Europäisches Patentamt  
European Patent Office  
Office européen des brevets

(11) Publication number:

**0 233 067**  
**A2**

(12)

# EUROPEAN PATENT APPLICATION

(21) Application number: 87301047.4

(51) Int. Cl.: C 08 F 8/42, A 61 L 15/00

(22) Date of filing: 05.02.87

(30) Priority: 05.02.86 JP 23462/86  
27.12.86 JP 31449/86

(71) Applicant: SEKISUI KASEIHIN KOGYO KABUSHIKI  
KAISHA, 25, 1-chome Minami Kyobate-cho, Nara-shi  
Nara 630 (JP)

(43) Date of publication of application: 19.08.87  
Bulletin 87/34

(72) Inventor: Shirai, Hideharu, No. 526-38, Hiramatsu-cho,  
Nara-shi Nara, 631 (JP)  
Inventor: Yamai, Fumito, No. 723-2, Shimogasa-cho,  
Kusatsu-shi Shiga, 525 (JP)  
Inventor: Inada, Setsuo, No. 6-3, Shichijonishi machi,  
Nara-shi Nara 630 (JP)  
Inventor: Ike, Hisashi, No. 8-1, Byakugoji-cho, Nara-shi  
Nara, 630 (JP)  
Inventor: Nakahara, Yoshitumi, No. 136-3, Sanjo-cho,  
Nara-shi Nara, 630 (JP)

(84) Designated Contracting States: BE DE FR GB NL

(74) Representative: Whalley, Kevin et al, MARKS &  
CLERK 57/60 Lincoln's Inn Fields, London WC2A 3LS  
(GB)

(54) Water-absorbent resin and process for producing the same.

(57) A water-absorbent resin of polyacrylic acid series characterized in that the resin has the crosslinked surface formed by reacting a powdery water-absorbent resin of polyacrylic acid series with an aluminium compound which can react with the powdery resin in the presence of polyhydric alcohol and water.

**EP 0 233 067 A2**

799P53770

WATER-ABSORBENT RESIN AND PROCESS FOR PRODUCING THE SAME

5           This invention relates to a water-absorbent resin and a process for producing the same. This invention relates, more particularly, to a water-insoluble, water-absorbent resin of polyacrylic acid series whose water-absorbing capability is improved.

10           Water-absorbent resins capable of highly absorbing water as water-absorbent and water-retentive materials have been currently used in such fields as sanitary supplies, medical supplies, cosmetics, agriculture, foods, civil engineering and construction, and household goods.

15           As disclosed in U.S. Pat. Nos. 4,076,663 and 4,090,013, such water-absorbent resins include crosslinked type polyethylene oxide, crosslinked polyvinyl alcohol, crosslinked type polyacrylic acid and its salt, cellulose-acrylic acid-grafted copolymer and its salts, and hydrolyzate of

20           starch-acrylonitrile-grafted copolymer, of which the water-absorbent resins of polyacrylic acid series have been widely used because of their excellent water-absorbing capability in terms of water absorption and the speed of water absorption.

25           Such water-absorbent resins of polyacrylic acid

series have been utilized in a form of powder which is produced by mechanically powdering a blockish polymer obtained by polymerization in order to increase the speed of water absorption. In response to the fact that, in particular, water-absorbent resins with a high speed of water absorption have currently been required, the resins with a larger surface area by pulverization are used because the speed of water absorption of water-absorbent resins is proportional to their surface area. However, the pulverization by mechanically powdering means causes water-absorbent resins to be cut in crosslink or to develop a solubilizate part, leading to an extremely deteriorated water-absorbing capability such as water absorption and the speed of water absorption. The pulverization also causes such a problem that film is liable to develop on the particle surface in contact with water, which causes an unlikely water penetration and a powder coagulation (a phenomenon of undissolved lump of flour) when water absorbing, resulting in an insufficient water-absorbing capability. For example, if a commercially available powdery water-absorbent resin is further mechanically powdered, its water-absorbing capability is deteriorated such that water absorption is lowered to about a half and it takes a time as long as 30 minutes to 24 hours to obtain a given water absorption with respect to the speed of

water absorption, causing the phenomenon of undissolved lump of flour to be likely developed. Such powdering to improve the speed of water absorption has been accompanied by such a disadvantage that a solubilization or the phenomenon of undissolved lump of flour due to cross-link cut is generated to extremely deteriorate the water-absorbing capability.

In Japanese Pat. Application laid open No. 168921/1982, a water-absorbent resin produced by coating a highly-water-absorbent macromolecular material such as cross linked polyacrylic acid salt, etc. with a water-soluble resin such as polyethylene glycol, etc. is disclosed which avoids the above-noted disadvantage and which generates no phenomenon of undissolved lump of flour and has a high speed of water absorption. However, when the resin is produced, it involves a uneconomical production process where the highly-water-absorbent macromolecular material powder is coated with the water-soluble resin dissolved in a large amount of an organic solvent such as methanol, etc. and then the large amount of the solvent is removed in vacuo, and it has difficulty to be industrially and safely produced because of utilization of organic solvent. When water was used instead of an organic solvent such as methanol, etc. and the highly-water-absorbent macromolecular material powder was coated with a mixture of

water and polyethylene glycol, the resultant water-absorbent resin generated the phenomenon of undissolved lump of flour and failed to increase the speed of water absorption.

5           In Japanese Pat. Application laid open No. 42602/  
1983, a method is disclosed which increases the speed of  
water absorption and prevents the phenomenon of undis-  
solved lump of flour by dispersing a hydrophilic-cross-  
linked polymer into a dispersing medium such as methanol  
10   and ethanol to further crosslink the resin surface with a  
crosslinking agent such as multivalent metal salt.  
However, even with that method, an uneconomical production  
process is required where the resin is surface treated  
using a large amount of a solvent such as methanol,  
15   ethanol, etc., filtered, and then vacuum dried for a long  
time to remove the solvent, leading to an insufficient  
improvement of the speed of water absorption and insuf-  
ficient prevention of the phenomenon of undissolved lump  
of flour when using only the crosslinking agent such as  
20   multivalent metal salt.

          Further, a water-absorbent resin is required to have  
such properties as a high gel strength after water absorb-  
ing and an excellent resin fluidity before water absorbing  
with regard to a workability when the end product using  
25   the water-absorbent resin is produced as well as an

excellent water absorption and the speed of water absorption. However, no prior water-absorbent resin of polyacrylic acid series has sufficiently satisfied these requirements.

5

It is accordingly an object of this invention to provide a water-absorbent resin having a highly-water-absorbing capability. More particularly, it is an object of this invention to provide a water-absorbent resin having a high-water-absorption and/or a high-speed of water absorption.

Another object of this invention is to provide a process for producing a water-absorbent resin having a highly-water-absorbing capability.

This invention, which has been completed as a result of an eager research by inventors, is directed to the provision of a water-absorbent resin of polyacrylic acid series characterized in that the resin has a crosslinked surface formed by reacting a powdery water-absorbent resin of polyacrylic acid series with aluminum compounds which can react with the resin in the presence of a polyhydric alcohol and water, and to the provision of a process for producing the same.

The water-absorbent resin of this invention is characterized in that it generates no phenomenon of undissolved lump of flour when water absorbing, has a high gel strength after water absorbing, and has a high resin fluidity before water absorbing.

The production method of the water-absorbent resin of this invention is further characterized in that it provides a water-absorbent resin having a highly-water-absorbing capability by a simple method without using an organic solvent such as lower alcohol.

Examples of the water-absorbent resins of polyacrylic acid series used in this invention as a raw material include polymers or copolymers whose main chain has at least a monomer unit of acrylic acid and/or acrylic acid salt; polysaccharide such as starch and cellulose-acrylic acid grafted copolymer and its salt, and the like.

The polymers or copolymers whose main chain has at least a monomer unit of acrylic acid and/or acrylic acid salt include polyacrylic acid, polyacrylic acid salt, and acrylic acid-acrylic acid salt copolymer. Examples of the salt moieties of the acrylic acid salt and polyacrylic acid salt can include alkali metal salts such as sodium



salt, potassium salt, lithium salt, etc. and organic base salts such as ammonium salt, triethylamine salt, pyridine salt, etc. These polymers may be the copolymers with acrylamide, N-vinyl pyrrolidone, 2-hydroxyethyl methacrylate, etc., in order to modify the characteristics such as hydrophilic as required. The raw polymers are preferably crosslinked ones which are produced by known crosslinking means. For example, the crosslinked copolymers are produced by crosslinking themselves by heating, by using a catalyst having an oxidative property such as potassium persulfate and the like, or by adding a crosslinking agent having two or more polymerizable unsaturated bonds such as N, N'-methylene-bis-acrylamide when performing polymerization. Those resins are usually produced by polymerization, as required, after adding the crosslinking agent and, other copolymerizable monomers to a water solution of acrylic acid and/or acrylic acid salt, and then are dried to form blockish resins which are thus powdered to an appropriate size by a grinder. The grain size is preferably 5 to 400 mesh and more preferably 10 to 200 mesh in terms of Tyler's standard sieve mesh. According to emulsion polymerization or suspension polymerization, small spherical particle polymers can be obtained. They may further be powdered.

Polysaccharide such as starch and cellulose-acrylic

acid grafted copolymers and their salts can be produced by conventional methods, for example, by the method disclosed in U.S. Pat. No. 4,076,663.

5       The water-absorbent resin of this invention has a crosslinked surface which is formed by reacting the powdery water-absorbent resin mentioned above with an aluminum compound that can react with the powdery resin in the presence of a polyhydric alcohol and water.

10       Examples of the polyhydric alcohol to be used in this invention are as follows: diol group including ethylene glycol, 1,2-propanediol, 1,3-propanediol, butanediols (such as 1,2-butanediol, 1,3-butanediol, 1,4-butanediol, 2,3-butanediol, etc.), pentanediols (such as 1,5-pentanediol, 1,3-pentanediol, 2,3-pentanediol, etc.),  
15       hexanediols (such as 1,6-hexanediol, 2,5-hexanediol, etc.), 2-methyl-2,4-pentanediol, 2-methyl-2,3-butanediol, etc.; triol group including glycerin, trimethylolpropane, hexanetriols (such as 1,2,6-hexanetriol, 1,3,5-hexanetriol, etc.), triethanolamine, etc.; tetraol group  
20       including pentaerythritol, diglycerin, etc.; pentaol group including glucose, furanose, etc.; hexaol group including sorbitol, mannitol, etc.; octaol group including sucrose, etc.; lower alkylene oxide addition product of the compounds mentioned just above; and lower alkylene oxide  
25       copolymers. These polyhydric alcohols may be used by

mixing two or more types of them. The lower alkylene oxides include alkylene oxides having 2 to 4 carbon atoms such as ethylene oxide ( hereinafter referred to as EO ), propylene oxide (hereinafter referred to as PO), butylene oxide, etc.

5 Examples of polyhydric alcohols to which these alkylene oxides are added are as follows: diethylene glycol, triethylene glycol, polyethylene glycols [mean molecular weight (hereinafter referred to as MW): 200, 300, 400, 600, 1000, 2000, 6000, etc.], dipropylene glycol, tri-

10 propylene glycol, polypropylene glycols [MW: 200, 400, 1000, 2000, 4000, etc.], glycerin-EO addition products [MW: 400, 600, 1000, 3000, 4000, etc.], glycerin-PO addition products [MW: 400, 600, 1000, 3000, 4000, etc.],

15 glycerin-EO (50)/PO(50) random addition products [MW: 2600, etc.], glycerin-PO(80)-EO(20) block addition products [MW: 3000, etc.], trimethylolpropane-EO addition product, trimethylolpropane-PO addition product, pentaerythritol-EO addition product, pentaerythritol-PO addition product, and sorbitol-EO addition product, etc.

20 The lower alkylene oxide copolymers include random copolymer and block copolymer, such as polypropylene glycol-EO addition products [MW: 2400, 3100, 4000, etc.].

Among these compounds, for example, glycerin-EO(50)/PO(50) random addition product denotes the compound in

25 which a mixture containing 50% EO and 50% PO by weight

(each % by weight being with reference to total alkylene oxide weight) is random added to glycerin, and glycerin-PO(80)-EO(20) block addition product denotes the compound in which PO of 80% by weight is added to glycerin and then  
5 EO of 20% by weight is added to the product ( each % by weight having the same meaning as defined above).

Preferable compounds among the polyhydric alcohols are ethylene glycol, propanediol, butanediol, pentanediol, hexanediol, 2-methyl-2,4-pentanediol, hexanetriol, gly-  
10 cerin, pentaerythritol, sorbitol, polyethylene glycol, polypropylene glycol, glycerin-EO addition product, glycerin-PO addition product, pentaerythritol-EO addition product, pentaerythritol-PO addition product, and sorbitol-EO addition product, and more preferable compounds  
15 among them are ethylene glycol, propanediol, butanediol, pentanediol, hexanediol, 2-methyl-2,4-pentanediol, hexanetriol, and polyethylene glycol.

The added quantity ratios of the polyhydric alcohols to the water absorbent resins range from 0.01 to 50% by  
20 weight, preferably from 0.1 to 20% by weight, and more preferably from 1 to 15% by weight. An added quantity ratio less than 0.01% by weight provides no addition effect, while an added quantity ratio exceeding 50% by weight causes lowered water absorption capability or  
25 reduced powder fluidity to provide an undesirable perfor-

mance.

Experiments showed that the water-absorbent resin of the invention produced using a compound, among the polyhydric alcohols, to which lower alkylene oxide was not added had an extremely good fluidity of the resin before water absorbing.

Aluminum compounds to be used as a crosslinking agent for the surface of water-absorbent resins of polyacrylic acid series in this invention may be the aluminum compounds which can react with the carboxyl group or carboxylate group of said water-absorbent resins, including aluminum salt such as aluminum chloride, aluminum nitrate, aluminum sulfate, aluminum phosphate, aluminum acetate, etc., aluminum hydroxide, aluminum alkoxide such as aluminum isopropoxide, aluminum ethoxide, aluminum-tertiary-butoxide, etc., two or more types of which may be mixed for use. Using aluminum compounds particularly in such state as aluminum hydroxide sol or aluminum hydroxide gel immediately after precipitation for crosslinking reaction enhances reactivity to allow the gel strength to increase without much deteriorating water absorption properties and can avoid the formation of unnecessary residues, providing a preferable condition. This condition can suitably be obtained by the reaction of aluminum salt with aluminate or by the reaction of aluminum salt with alkali metal

hydroxide in the presence of water.

The aluminum compounds are added to water-absorbent resins in added quantity ratios of 1 to 40% by weight, preferably 0.5 to 25% by weight, and more preferably 1 to 5 15% by weight. An added quantity ratio less than 0.1% by weight gives an insufficient crosslinking not to prevent the phenomenon of undissolved lump of flour, while a ratio exceeding 40% by weight gives an excessive surface crosslinking, resulting in lowered water absorption.

10 The water to be used in this invention, which is not particularly specified, may be ion exchanged water, distilled water, city water, etc. and the quantity of water to be used may be large or larger enough to dissolve or disperse the aluminum compound, usually about 1 to 10 15 times the quantity of aluminum compound (by weight), preferably 1 to 8 times, and more preferably 2 to 6 times.

The water-absorbent resin in this invention is produced by treating a powdery water-absorbent resin of polyacrylic acid series with the aluminum compound which 20 can react with said powdery resin in the presence of the polyhydric alcohol and water to crosslink the surface of said water-absorbent resin. More particularly, for example, the resin is produced by mixing said powdery water-absorbent resin of polyacrylic acid series with the 25 aluminum compound in the presence of the polyhydric

alcohol and water. The mixing means, which is not particularly limited, can use such conventional mixers as Nauta mixer, ribbon blender, conical blender, Henshel mixer and Raikai mixer. For example, the water-absorbent resin is produced by such a method that said resin is added into a mixer, and a solution in which a desired quantity of the polyhydric alcohol and the aluminum compound is dissolved (or dispersed) in water is admixed or sprayed in the mixer while stirring to provide a sufficient mixing, and finally the resultant mixture is dried by a dryer. A method may be used that respective water solutions (or dispersed solutions) for polyhydric alcohol and for aluminum compound are prepared, and both the solutions are simultaneously added to said resin, or either polyhydric alcohol solution or aluminum compound solution is added and then the remaining solution is added to said resin.

In the above production processes, the reaction temperature, which is not particularly limited, is usually from room temperature to 100°C, and preferably from room temperature to 60°C, and the reaction time is 1 to 120 minutes, and preferably 2 to 30 minutes. Drying is performed by using such conventional dryers as circulating hot air dryer and vacuum dryer, and the drying temperature is from room temperature to 150°C, and preferably from 70 to 120°C. In order to improve the fluidity and

crosslinking properties while stirring, calcium chloride and zinc nitrate may be added to the mixture.

The most preferable, practical procedures of the preparation method of the crosslinking agent solution used for producing the water-absorbent resin in this invention are as follows:

(A) Where aluminum chloride and sodium aluminate are used as aluminum compounds:

(1) Eight parts by weight of aluminum chloride hexahydrate is added to 85 parts by weight of water while stirring to effect dissolution.

(2) Then, 8 parts by weight of sodium aluminate is gradually added while stirring.

(3) Aluminum hydroxide is at once formed to give a cloudy appearance for the mixture, and the viscosity once extremely increases to lose the fluidity, but continuing stirring causes the mixture to have again the fluidity, becoming a viscous solution. A stirring time more than 20 minutes is usually preferable.

(4) Fifteen parts by weight of the polyhydric alcohol is added to the solution, and stirred to obtain an uniform solution, allowing the crosslinking agent solution to be prepared. The polyhydric alcohol may be added to the original water.

(B) Where aluminum chloride and alkali metal



hydroxide such as sodium hydroxide are used as an aluminum compound:

(1) Fifteen point nine parts by weight of sodium hydroxide is dissolved in 85 parts by weight of water.

5 (2) Then, 32 parts by weight of aluminum chloride hexahydrate is gradually added while stirring.

(3) The subsequent procedures are performed in a similar manner to (3) and (4) of the method (A) mentioned above.

10 The crosslinking agent solution prepared in such manners is used preferably in the ratio of 100 to 300 parts by weight of powdered water-absorbent resin of polyacrylic acid series to 100 parts by weight of said solution. Since, if the crosslinking agent solution is left to stand, aluminum hydroxide precipitates to be  
15 separated from the solution, the solution is used preferably in a stirred and dispersed state.

The water-absorbent resins of this invention are used in a form of powder, whose grain size is about 5 to 500 mesh, and preferably 10 to 200 mesh in terms of Tyler's  
20 standard sieve mesh. The resins may be used, as required, containing such admixtures as fluidity assisting agents including impalpable powder silica and talc, bulking filter, antioxidant, fungicide, bactericide, perfume, colorant, and deodorant. The water-absorbent resins of  
25 this invention can be used in a similar manner to prior

water-absorbent resins.

This invention has various features, for example:

- (1) The water-absorbent resins of this invention exhibit a high water absorption and high speed of water absorption not only for water but also for solutions containing salts such as human body excrement liquid including urine and blood. Prior water-absorbent resins have involved a problem of low water absorption capability for salt solutions, while the water-absorbent resins of this invention can promptly absorb the urine and blood. A high gel strength after water absorbing allows said resins to retain water content in a stable shape, providing an excellent water retention characteristics.
- (2) The water-absorbent resins of this invention generate no phenomenon of undissolved lump of flour when water absorbing, permitting the speed of water absorption to extremely increase.
- (3) Prior water-absorbent resins, which lack the fluidity in a state before water absorbing, have involved various troubles such that a feeding port is clogged with the resins or an uniform spraying of the resins on products cannot be performed when producing the end products using water-absorbent resins including paper diapers and sanitary napkins, while the water-absorbent resins of this invention, which exhibit a high fluidity before water

absorbing, have an advantage of excellent workability.

(4) The process for producing the water-absorbent resins of this invention makes it possible to produce the water-absorbent resins having an excellent water absorption capability in a simple and economical manner. This means that prior production methods use a large quantity of organic solvent such as alcohol having combustible, explosive and toxic properties in coating and crosslinking processes, and require filtering, drying and solvent recovering processes; while the production method of this invention, which uses no organic solvent and provides the water-absorbent resins in a simple operation, offers a simple production process and reduced cost, and can safely and industrially produce the water-absorbent resins.

The water-absorbent resins of this invention have high water absorption and high speed of water absorption as well as an excellent water retention characteristics and gel strength. They, therefore, can be utilized for various applications, for example, sanitary supplies such as paper diapers, catamenial tampons, sanitary napkins and paper towels, medical supplies such as water retainers of cataplasm, agricultural supplies such as seed germination assisting agents and soil water retainers, building supplies such as dew condensation preventing materials for interior portions, and cosmetics supplies such as water

retainers of cosmetics and perfumes.

#### EXAMPLES

5 Hereinafter, this invention will be described in greater detail with reference to Comparative Examples and Examples. However, this invention is not limited to these Examples. Percent in the Examples is by weight unless otherwise specified.

10 The tests of water-absorbent resins were conducted in the following methods:

a) measurement of water absorption

15 A sample (Xg) is put into a commercially available coffee filter, which is folded, and dipped into a 0.9% saline solution for a given time, and then the weight (Yg) including the coffee filter is measured. With the weight (Zg) of the wet coffee filter itself measured beforehand, the water absorption (times) is determined by the following equation:

$$\text{Water absorption (times)} = (Y - Z) / X$$

20 b) Measurement of gel strength

Ninety eight grams of a 0.9% saline solution is added to a 200 ml beaker to effect gel formation through addition of 2g of a water-absorbent resin while stirring by a magnetic stirrer. After the resultant gel has been left  
25 to stand for 24 hours, the steel balls of the ball

bearings to JIS Standard whose diameter increases by 1/16 inch increments from a 3/16 inch diameter are sequentially placed on the gel surface until they settle in the gel. However, the ball having not settled is removed before the subsequent ball is placed. With such procedures, the maximum diameter of the ball having not settled is defined as the gel strength of the resin.

c) Measurement of fluidity

Using a hollow cylindrical vessel (with an inside diameter of 43 mm) having a bottom plate whose center part has a circular hole (with a diameter of 15 mm), 150 ml of a dry water-absorbent resin is added to the vessel with the circular hole closed. Then the circular hole is opened to allow the water-absorbent resin to be dropped. After the dropping has ended, an angle formed by the surface of the residual resin in the vessel and the bottom plate is measured, and the angle is defined as the fluidity of the resin.

COMPARATIVE EXAMPLE 1

A 20% water solution (25 parts by weight) of each aluminum compound shown in Table I was added while highly stirring to 100 parts by weight of the mechanically, finely-ground resin from a powdered water-absorbent resin [whose trade name: AQUAKEEP 10 SH, by Steel Chemical Co., Ltd. (Japan)] which is a commercially available,

self-crosslinking type resin of sodium polyacrylate series  
produced by a reverse phase suspension polymerization  
technique. After stirring for 2 to 3 minutes, the resin  
was dried to about 7% in water content. The water absorp-  
5 tion characteristics test of each resin obtained in such  
manner was conducted. The results are shown in Table I.

As shown in Table I, if a water solution consisting  
of only an aluminum compound without containing any poly-  
hydric alcohol is used, a water-absorbent resin is  
10 coagulated or bonded when mixing is performed to provide a  
difficulty in kneading, and the phenomenon of undissolved  
lump of flour is likely to develop when water absorbing.  
The speed of water absorption is also insufficient.

15

20

25

Table I

Aluminum compounds	Water absorption (times)					Remarks
	Time (minute)					
	3	5	10	30		
Aluminum isopropoxide	20	40	60	70 (equilibrium)		Finely powdered granules are coagulated and bonded when mixing. A phenomenon of undissolved lump of flour develops when water absorbing.
S dium aluminate	30	45	50	60 (equilibrium)		
Aluminum chloride hexahydrate	30	45	50	60 (equilibrium)		
Same weight mixture of sodium aluminate and aluminum chloride hexahydrate	25	45	60	70 (equilibrium)		Finely powdered granules are coagulated and bonded when mixing.
Same weight mixture of sodium aluminate and calcium chloride hexahydrate	25	40	50	60 (equilibrium)		A phenomenon of undissolved lump of flour develops when water absorbing.
Same weight mixture of sodium aluminate and zinc nitrate hexahydrate	25	40	50	60 (equilibrium)		

EXAMPLE 1

Using water solutions with the following composition utilizing polyethylene glycols of respective molecular weight and aluminum compounds shown in Table II instead of the 20% water solution of aluminum compounds in Comparative example 1, water-absorbent resins were produced with a similar quantity to be used and operation to that in Comparative example 1. The water absorption capability of the resultant water-absorbent resins was measured. The results are shown in Table II. The mixture of the finely powdered water-absorbent resin granules as a raw material with the water solution was powdery without rapidly stirring, and the finely powdered granules were not coagulates and bonded, providing an extremely good mixing characteristics. Where particularly aluminum isopropoxide or the same weight mixture of sodium aluminate and sodium chloride as an aluminum compound was used, the state of the resin before being dried was nearly equal to that of the dried resin. The water retention characteristics of the resins after absorbing water were extremely good for each case.

Water solution composition

Total quantity of aluminum compounds:

20 parts by weight

Polyethylene glycol: 8 . "

ion exchanged water: 72 "



Table II

Example No.	Aluminum compounds	Type of polyethylene glycol (PEG)	Water absorption (equilibrium)
1-1	Aluminum isopropoxide	PEG 400	70 ~ 75 times (after 3 min.)
		PEG 2000	Ditto
		PLA 6000	60 times (within 3 min.)
1-2	Sodium aluminate	PEG 400	65 times (after 5 min.)
		PEG 2000	Ditto
		PEG 6000	50 times (within 3 min.)
1-3	Aluminum chloride hexahydrate	PEG 400	65 times (after 5 min.)
		PEG 2000	Ditto
		PEG 6000	50 times (within 3 min.)
1-4	Same weight mixture of sodium aluminate and aluminum chloride hexahydrate	PEG 400	70 ~ 75 times (after 3 min.)
		PEG 2000	Ditto
		PEG 6000	60 times (within 3 min.)
1-5	Same weight mixture of sodium aluminate and calcium chloride hexahydrate	PEG 400	60 times (after 3 min.)
		PEG 2000	Ditto
		PEG 6000	50 times (within 3 min.)
1-6	Same weight mixture of sodium aluminate and zinc nitrate hexahydrate	PEG 400	60 times (after 3 min.)
		PEG 2000	Ditto
		PEG 6000	50 times (within 3 min.)
1-7	Water solution of aluminum sol	PEG 400	85 times (within 2 min.)
		PEG 2000	Ditto
		PEG 6000	70 times (within 2 min.)

## Example 2

Thirty grams of acrylic acid was neutralized with 75g of a 20% water solution of sodium hydroxide, and at the same time was mixed with 0.9g of acrylamide added. Three  
5 grams of a 1% water solution of sodium dithionite as a catalyst was first added to the mixture, and after 30 seconds 2g of a 1% water solution of potassium persulfate and 2g of a 1% water solution of aluminum nitrate were  
10 added to the mixture, which was stirred for about 30 seconds and then was left to stand to effect polymerization. When the polymerization was performed, the system did not particularly indicated an increased temperature. The resultant polymer was hardened to a plate shape by being dewatered and dried in a circulating hot air dryer at  
15 100°C for 24 hours. Then, the hardened polymer was powdered to be sieved with a Tayler's standard sieve of 80 mesh.

One hundred parts by weight of a crosslinking agent compound with a composition shown in Table III was added  
20 to 100 parts by weight of the resultant powdery product passing through the 80 mesh sieve and was mixed together, and then the resultant powder was dewatered and dried in a circulating hot air dryer at 100°C for 30 minutes. The water absorption capability of the resultant resin is as  
25 shown in Table III.

As Comparative examples 2 to 5, the data using the composition containing no polyethylene glycol, aluminum compound and the like are together shown in the Table.

5

10

15

20

25

0233067

Table III

Composition (weight ratio)					Water absorption (times)						
					Time (minute)						
					3		5	10	20	30	60
					30		36	50	55	58	61
Example 2					The mixture exhibits a blocking (dumpling state), making measurement impossible.						
Comparative example No.	2	3	17	Aluminum chloride hexahydrate	Sodium aluminate						
	3	---	20	0.30	0.33						
	4	20	--	0.30	0,33	--	--	7	8	10	12
	5	---	--	----	----	6	6	6	8	10	12

EXAMPLE 3

Thirty grams of acrylic acid was neutralized with 75g of a 20% water solution of sodium hydroxide, and at the same time was added 0.9g of acrylamide with stirring. 5 Three grams of a 1% water solution of potassium persulfate as a catalyst was added to the mixture, which was stirred for about 30 seconds and then was left to stand on bath at 60°C for 1 hour to effect polymerization. The resultant polymer was hardened to a plate shape by being dewatered 10 and dried in a circulating hot air dryer at 100°C for 24 hours. Then, the hardened polymer was powdered to be sieved with a Tyler's standard sieve of 80 mesh.

One hundred and fifty parts by weight of the resultant powdered product passing through the 80 mesh sieve 15 was charged into a Raikai mixer, and 75 parts by weight of a crosslinking agent with a composition shown below was added to the product while stirring and was mixed together for 20 minutes, and then the resultant powder in a wet state was dried in a circulating hot air dryer at 100°C 20 for 1.5 hours to obtain a water-absorbent resin.

Crosslinking agent composition

(1) Ion exchanged water:

85 parts by weight

(2) Polyhydric alcohol:

15 "

25

(3) Aluminum chloride hexahydrate:

8 parts by weight

(4) Sodium aluminate: 8 "

5 The tests of the water absorption (speed of water absorption), the gel strength after water absorbing and the resin fluidity before water absorbing on the resultant water-absorbent resins were conducted. The results are shown in Table IV.

10 As Comparative example 6, a water-absorbent resin was produced in a similar manner to Example 3 using a compound having 100 parts by weight of ion exchanged water except the polyhydric alcohol in the crosslinking agent composition, and its water absorption capability was examined. The result is together shown in Table IV.

15

#### EXAMPLE 4

20 A water-absorbent resin was produced in a similar manner to Example 3 except that the crosslinking agent composition shown in Table V was used. The tests of the water absorption (speed of water absorption), the gel strength after water absorbing and the resin fluidity before water absorbing on the resultant water-absorbent resins were conducted. The results are shown in Table V.

25 It will be apparent that the water-absorbent resins of this invention, as shown in Tables IV and V, exhibit an

excellent property in terms of the gel strength after water absorbing and the fluidity of water-absorbent resins as well as in terms of water absorption and the speed of water absorption.

5           All the water-absorbent resins obtained in Comparative examples 1 to 6 have poor hydro-extraction properties to make a correct measurement of water absorption difficult, providing an approximate value for the units digit of the measured values of water absorption.

10

15

20

25

Table IV

Example No.	Polyhydric alcohols	Water absorption (times)						Gel strength (inch)	Fluidity (degree)
		Time (minute)							
		3	5	10	20	30	60		
3-1	1,3-butanediol	57	60	63	66	66	67	10/16	36
3-2	1,5-pentanediol	59	60	64	65	65	65	9/16	40
3-3	2-methyl-2-4-pentanediol	61	63	63	63	64	64	8/16	37
3-4	1,2,6-hexanetriol	56	57	59	59	59	60	9/16	40
Comparative example 6	-----	35	40	50		60		3/16 or less	

Table V

Example No.	Crosslinking agent composition Figures in parentheses indicate parts by weight.		Water absorption (times)								Gel strength (inch)	Fluidity (degree)
			Time (minutes)									
			3	5	10	20	30	60				
4-1	Water (85)	1,3-butanediol (15)	AlCl <sub>3</sub> • 6H <sub>2</sub> O + NaOH (32) (15.9)		58	61	64	67	69	69	9/16	37
4-2	Ditto	Ditto	Al (OH) <sub>3</sub> (10)		50	54	54	57	59	60	4/16	40
4-3	Ditto	Ditto	AlCl <sub>3</sub> • 6H <sub>2</sub> O (31)		49	52	53	55	57	57	5/16	42
4-4	Ditto	Ditto	Aluminum isopropoxide (26)		54	57	60	62	64	66	5/16	41
4-5	Ditto	Polyethylene glycol (MW 2000) (15)	AlCl <sub>3</sub> • 6H <sub>2</sub> O + NaAlO <sub>2</sub> (8) (8)		57	60	64	68	68	70	8/16	58



## CLAIMS

1. A water-absorbent resin of polyacrylic acid series,  
characterized in that said resin has the crosslinked  
surface formed by reacting a powdery water-absorbent  
5 resin of polyacrylic acid series with an aluminium  
compound which can react with said powdery resin in the  
presence of a polyhydric alcohol and water.
2. A water-absorbent resin as claimed in claim 1,  
characterized in that said water-absorbent resin of  
10 polyacrylic acid series is a crosslinked product of  
polymer whose main chain has, at least, a monomer unit  
of acrylic acid and/or acrylic acid alkali metal salt.
3. A water-absorbent resin as claimed in claim 2,  
characterized in that the aluminium compound is a salt,  
15 hydroxide and/or alkoxide of aluminium.
4. A water-absorbent resin as claimed in claim 3,  
characterized in that the aluminium compound is one or a  
mixture of two or more types, selected from aluminium  
chloride, aluminium nitrate, aluminium sulfate,  
20 aluminium phosphate, aluminium hydroxide, aluminium  
isopropoxide, aluminium ethoxide, and aluminium-  
tertiary-butoxide.

5. A water-absorbent resin as claimed in claim 4, characterized in that the aluminium compound is an aluminium hydroxide gel formed by the reaction of aluminium salt with aluminate salt, or by the reaction of aluminium salt with alkali metal hydroxide.
6. A water-absorbent resin as claimed in any of claims 2 to 5, characterized in that the polyhydric alcohol is one or a mixture of two or more types, selected from ethylene glycol, propanediol, butanediol, pentanediol, hexanediol, 2-methyl-2,4-pentanediol, hexanetriol, glycerin, pentaerythritol, sorbitol, polyethylene glycol, polypropylene glycol, glycerin-EO addition product, glycerin-PO-addition product, pentaerythritol-EO addition product, pentaerythritol-PO addition product, and sorbitol-EO addition product.
7. A water-absorbent resin as claimed in claim 1, characterized in that said water-absorbent resin of polyacrylic acid series is a polysaccharide-acrylic acid graft copolymer or its salt.
8. A water-absorbent resin as claimed in any of claims 1 to 7, characterized in that the added quantity ratio of polyhydric alcohol is 0.01 to 50% by weight, and the added quantity ratio of aluminium compound is 0.1 to 40% by weight to said powdery water-absorbent resin of polyacrylic acid series.

9. A water-absorbent resin as claimed in claim 8, characterized in that the added quantity ratio of polyhydric alcohol is 0.1 to 20% by weight, and the added quantity ratio of aluminium compound is 0.5 to 25% by weight to said powdery water-absorbent resin of polyacrylic acid series.

10. A water-absorbent resin as claimed in claim 9, characterized in that the added quantity ratio of polyhydric alcohol is 1 to 15% by weight, and the added quantity ratio of aluminium compound is 1 to 15% by weight to said powdery water-absorbent resin of polyacrylic acid series.

11. A process for producing a water-absorbent resin of polyacrylic acid series, characterized in that a powdery water-absorbent resin of polyacrylic acid series is treated with an aluminium compound which can react with said powdery resin in the presence of polyhydric alcohol and water.

12. A process as claimed in claim 11, characterized in that said water-absorbent resin of polyacrylic acid series is a crosslinked product of polymer whose main chain has, at least, a monomer unit of acrylic acid and/or acrylic acid alkali metal salt.